


Origine/Origin

Chine/China

Composition/Samenstelling

Contreplaqué/Veneer/Fineer :	Sapeli FSC
Qualité/Quality/Kwaliteit	B/BB
Cœur/Core/Kern :	+50% Eucalyptus -50% Poplar/peuplier/poplar
Colle/Glue/Lijm :	WBP/E1 (formaldehyde bas/low/laag) (EN13986 annex B)
Qualité colle/glue/lijm	Classe 2 (EN314-1&2 : 1993-
Qualité surface/Quality/Kwaliteit	2xpressé/pressed/geperst 3x poncé/sanded/geschuurd
Qualité performance panneau/panel/paneel	Trous rempli/holes filled/gaten gevuld CE2+

Utilisation/Use/Gebruik

Usage interne humide/Humid indoor use/Vochtig binnenshuis gebruik	(EN636-2)
Usage interne sec/Dry indoor use/Droog Binnenshuis gebruik	(EN636-1)

Caractéristiques/Specifications/Kenmerken (EN13986:2004 + A1:2015)

Épaisseur/thickness/dikte	Unit	5.5	9	12	15	18	25	Tech spec
Résistance à la flexion Bending strength/plooiesterkte	N/mm ²	45.30 54.00	48.50 56.70	51.40 53.80	47.10 54.60	41.90 52.00	52.20 52.60	EN310:1993
Rigidité en flexion/Bending stiffness/plooiestijfheid	N/mm ²	4750 6842	4736 6764	4939 6978	4739 6627	4802 6562	4885 6772	EN310:1993
Teneur en humidité/Moisture content	%	10.2	10.2	10	10.2	10.6	10.3	EN322:1993
Réaction au feu/reaction to fire	Class		D- s2,d0	D- s2,d0	D- s2,d0	D- s2,d0	D- s2,d0	EN13986:2004+A1:2015
Perméabilité à la vapeur d'eau/water vapour permeability	Wet cup Dry cup		90u 220u	90u 220u	70u 200u	70u 200u	70u 200u	EN13986:2004+A1:2015
Thermal conductivity	W/(m.k)		0.18	0.18	0.14	0.14	0.14	EN13986:2004+A1:2015

* basé sur DOP test, peut différer un peu entre tests (based on DOP-test, can have minor differences between tests)

Densité/Density/Densiteit:	590kg/m ³	(EN323)
Dimension Tolérance/Tolerance/Tolerantie:	±0.5mm	
Déformation/Warp/Werken:	<1%	

Dimensions/Dimensions/Afmetingen (stock)

Dimensions	Pcs/p	EAN	SAP	HS (instrastat)
3.6x2500x1220mm	270	5425034260339	A000090	44123110
5x2500x1220mm	180	5425034260346	A000091	44123110
8x2500x1220mm	115	5425034260353	A000092	44123110
10x2500x1220mm	90	5425034260360	A000093	44123110
12x2500x1220mm	75	5425034260377	A000094	44123110
15x2500x1220mm	60	5425034260384	A000095	44123110
18x2500x1220mm	50	5425034260391	A000096	44123110
21x2500x1220mm	41	5425034260407	A000097	44123110
25x2500x1220mm	36	5425034260414	A000098	44123110
30x2500x1220mm	30	5425034260421	A000099	44123110
35x2500x1220mm	27	5425034260438	A000100	44123110
40x2500x1220mm	22	5425034260445	A000101	44123110

scier sur demande/sawing on demand/zaagwerk op aanvraag

Dimensions	Pcs/p	EAN	SAP	HS (instratat)
5x3050x1530mm	134	5425034260452	A000102	44123110
8x3050x1530mm	80	5425034260469	A000103	44123110
10x3050x1530mm	67	5425034260476	A000104	44123110
12x3050x1530mm	56	5425034260483	A000105	44123110
15x3050x1530mm	45	5425034260490	A000106	44123110
18x3050x1530mm	38	5425034260506	A000107	44123110
21x3050x1530mm	33	5425034260513	A000108	44123110
25x3050x1530mm	26	5425034260520	A000109	44123110
30x3050x1530mm	23	5425034260537	A000110	44123110
35x3050x1530mm	20	5425034260544	A000111	44123110
40x3050x1530mm	18	5425034260551	A000112	44123110

scier sur demande/sawing on demand/zaagwerk op aanvraag

Certificats & écology/Certificats & ecology

EUTR (sylviculture légale/legal forestry, CARB, CE2+, DOP, (FSC sur demande)